

Intertek Labtest

TEST REPORT

NUMBER: SZHJ08591004

APPLICANT:

GLORY MANUFACTURING
ROOM 706-8, KIN WING BLDG
24-30 KIN WING ST
TUEN MUN, NEW TERR, HONG KONG

DATE: Nov 27, 2006

SAMPLE DESCRIPTION:

ONE (1) SUBMITTED SAMPLE SAID TO BE SILVER COLOR METAL WITH DARK BROWN COATING (黑朱古力粉末样板).

FACTORY: 诚尚五金家具有限公司

BUYER: E & S


COUNTRY OF ORIGIN: CHINA

TESTS CONDUCTED:

AS REQUESTED BY THE APPLICANT, FOR DETAILS REFER TO ATTACHED PAGE(S)

REMARK: AS REQUESTED BY THE APPLICANT, COATING WITH BASE MATERIAL OF SUBMITTED SAMPLE WAS TESTED TOGETHER

AUTHORIZED BY:
FOR INTERTEK TESTING SERVICES
SHENZHEN LTD.



BEN N. L. LIN
GENERAL MANAGER



TEST REPORT

NUMBER: SZHJ08591004

TESTS CONDUCTED

(A) TEST RESULT SUMMARY FOR ROHS DIRECTIVE :

| TESTING ITEM | RESULT |
|---|---------|
| CADMIUM (Cd) CONTENT (ppm) | ND (<2) |
| LEAD (Pb) CONTENT (ppm) | ND (<2) |
| MERCURY (Hg) CONTENT (ppm) | ND (<2) |
| CHROMIUM (VI) (Cr ⁶⁺) CONTENT (ppm) | ND (<1) |

ppm = PARTS PER MILLION
 < = LESS THAN
 ND = NOT DETECTED

(B) ROHS REQUIREMENT

| RESTRICTED SUBSTANCES | LIMITS |
|-----------------------------------|-----------------|
| CADMIUM (Cd) | 0.01% (100 ppm) |
| LEAD (Pb) | 0.1% (1000 ppm) |
| MERCURY (Hg) | 0.1% (1000 ppm) |
| CHROMIUM (VI) (Cr ⁶⁺) | 0.1% (1000 ppm) |

THE ABOVE LIMITS WERE QUOTED FROM 2002/95/EC AND AMENDMENT 2005/618/EC FOR HOMOGENEOUS MATERIAL.

(C) TEST METHOD :

| TESTING ITEM | TESTING METHOD | REPORTING LIMIT |
|---|--|-----------------|
| CADMIUM (Cd) CONTENT | WITH REFERENCE TO BS EN1122 / US EPA 3050B / US EPA 3052, BY ACID DIGESTION AND DETERMINED BY ICP-OES | 2 ppm |
| LEAD (Pb) CONTENT | WITH REFERENCE TO US EPA 3050B / US EPA 3052, BY ACID DIGESTION AND DETERMINED BY ICP - OES | 2 ppm |
| MERCURY (Hg) CONTENT | WITH REFERENCE TO US EPA 3052, BY ACID DIGESTION AND DETERMINED BY ICP - OES | 2 ppm |
| CHROMIUM (VI) (Cr ⁶⁺) CONTENT | WITH REFERENCE TO US EPA 3060A & 7196A, BY ALKALINE DIGESTION AND DETERMINED BY UV-VIS SPECTROPHOTOMETER | 1 ppm |

DATE SAMPLE RECEIVED : NOV 20, 2006 & NOV 24, 2006
 TESTING PERIOD : NOV 20, 2006 TO NOV 25, 2006

 END OF REPORT